



# L/BA SBR

BIANCA (D.M. 174)

FDA



- È conforme ai decreti ministeriali 174 del 6/4/2004 e 21/3/1973 e alla lista FDA 177.2600.

It complies with the ministerial decrees 174 dated 6/4/2004 and FDA dated 21/3/1973.



## IMPIEGO APPLICATIONS

Idonea a contatto negli impianti fissi di captazione, trattamento, adduzione e distribuzione delle acque destinate al consumo umano. È conforme al decreto ministeriale 174 del 6/4/2004 e 21/3/1973 e alla lista FDA 177.2600. Non è indicata a contatto di sostanze oleose o grasse. Particolarmente consigliata quando si richiedono esigenze di pulizia ed estetica, infatti questa gomma non macchia. Disponibile il certificato di alimentarietà.

**Superficie:** Liscia/Liscia o a richiesta I.T./I.T.

Can be used in contact with stationary captation systems, treatment, carrying and distribution of water intended for human consumption. It complies with the ministerial decree 174 dated 6/4/2004 and 21/3/1973 and the FDA-list 177.2600. It is not suitable for contact with oily or greasy substances. In particular, it is recommended for strict hygiene and aesthetic requirements. In fact, this rubber is stain-proof. Food safety certificate available.

**Surface:** Smooth/Smooth or on request I.T./I.T.



## STOCK

mm



m



m

1/1,5/2	✓	1,4	10
2,5	--	1,4	10
3+8	✓	1,4	10
10	✓	1,4	5
12/15	--	1,4	5
20	✓	1,4	5
25+50	--	1	1



## DUREZZA HARDNESS

Norme / Norms:  
ASTM D2240

60 Shore A ± 5



## CARICO ROTTURA TENSILE STRENGTH

Norme / Norms:  
ASTM D412

80 kg/cm<sup>2</sup>



## ALLUNGAMENTO ELONGATION

Norme / Norms:  
ASTM D412

250%

Dichiarazione di conformità disponibile.

Declaration of compliance is available.



1,5 gr/cm<sup>3</sup>



-25°C / +80°C  
-13°F / +176°F