

L/EA EPDM BIANCA



- **Conforme alla lista FDA 177.2600, DM 174, DM 21/03/73 e CE 1935/2004**
- **It complies with the FDA list 177.2600, DM 174, DM 21/03/73 and CE 1935/2004**



IMPIEGO APPLICATIONS

Conforme alla normativa FDA 177.2600 e al DM 21/03/73 (simulante B ed Etanolo 15%) e succ. modifiche. Idonea a contatto negli impianti fissi di captazione, trattamento, adduzione e distribuzione delle acque destinate al consumo umano secondo DM 174 e al Regolamento Europeo CE 1935/2004. Particolarmente indicata in presenza di temperatura oltre 100°C. Ottima resistenza all'ozono, agenti atmosferici ed acqua di mare.
Superficie: Liscia/Liscia o a richiesta I.T./I.T.

It complies with the FDA list 177.2600 and DM 21/03/73 (simulant B and ethanol 15%) as amended.




Suitable for contact in fixed systems for the capture, treatment, conveyance and distribution of water intended for human consumption in accordance with Italian Ministerial Decree (DM) 174 and CE Regulation 1935/2004.

It is indicated in the presence of temperatures over 100°C. Excellent resistance against ozone, atmospheric agents and seawater.

Surface: Smooth/Smooth or on request I.T./I.T.

Dichiarazione di conformità disponibile.

Declaration of compliance is available.

 STOCK	 m	 m
mm	m	m
1	--	1,4
1,5	--	1,4
2 / 2,5	--	1,4
3 ÷ 10	--	1,4
12 ÷ 20	--	1,4
25 ÷ 50	--	1



DUREZZA HARDNESS

Norme / Norms:
ASTM D2240

60 Shore A ± 5



CARICO ROTTURA TENSILE STRENGTH

Norme / Norms:
ASTM D412

100 kg/cm²



ALLUNGAMENTO ELONGATION

Norme / Norms:
ASTM D412

300%



1,25 gr/cm³



-30°C / +120°C
-22°F / +248°F